



TESTING REPORT

SOFTLINE | LABORATORY

Report n° : ASCNLAB2311202

From : **AS CHINA**
Contact : Mason Shu
Phone : +86 182 1713 0680
Email : as.asia.testing@as-inter.com


To : **SAM**
Contact : /
Phone : /
Email : /

PRODUCT INFORMATION

The following sample(s) was/were submitted and identified by client as:

Supplier : SHANTOU UNIGRACE
MANUFACTURING LTD
Reference : PAILLETTE
Color(s) : BLUE
Order(s) : SAM200037/SAM2
00038
Sample description : PTINT MICRO/SELVEDGE
MESH/ STRETCH MESH

Sub. Care Instruction



Received date : 23/11/2020
Testing date : 23/11/2020
Report release : 26/11/2020

Sub. fiber content : /

Testing Number : 1
Carton No - Picking : /

CONCLUSION

Selected test(s) as requested by applicant

| TESTING | No | TOLERANCE(S) | RESULT | COMMENTS |
|---------------------------|-----|------------------------|--------|--|
| COLOR FASTNESS TO WASHING | 001 | Dark :3- 4 Other: 4 | PASSED | See testing details - Within acceptable tolerances |
| | 002 | | PASSED | See testing details - Within acceptable tolerances |
| | 003 | | PASSED | See testing details - Within acceptable tolerances |
| AZO | 001 | <30 mg/kg | PASSED | See testing details - Within acceptable tolerances |
| | 002 | | PASSED | See testing details - Within acceptable tolerances |
| | 003 | | PASSED | See testing details - Within acceptable tolerances |

CONCLUSION

The submitted sample (s) are correspond to client's requirements.

Authorized by: Mason SHU

Prepared by: Sandy ZHOU



Note: (1) General Terms & Conditions as mentioned overleaf. (2)The results relate only to the items tested. (3)The test report shall not be reproduced except in full without the written approval of the laboratory. (4) Samples are tested as received. (5) This testing report might contains testing and analysis subcontracted to certified premises.expressing by * .(6)The client takes full responsible for the truthfulness of the testing sample(s) and information related
Customer Service :

AS CHINA
Kunhua International Plaza
58 Hengshan Road
Building 3, Floor 26th,Room 2603-2605
215300, Kunshan city, Jiangsu province

Phone : +86 (0512) 5521 8316
Email : as.asia.testing@as-inter.com
Web : www.as-inter.com



TESTING REPORT

Softline | Laboratory

Report n° :

ASCNLAB2311202

TESTING DETAILS

COLOR FASTNESS TO WASHING

| Standard(s) | METHOD | | | | | | | | | TOLERANCE | | |
|------------------|--|-----|-----|--|--|--|--|--|--|------------------------|--|--|
| ISO 105-C06:2010 | A2S without steel balls | | | | | | | | | Dark :3- 4 Other: 4 | | |
| ITEM | 001 | 002 | 003 | | | | | | | | | |
| Colour change | 4-5 | 4-5 | 4-5 | | | | | | | | | |
| Cross staining | 4-5 | / | / | | | | | | | | | |
| Colour staining | | | | | | | | | | | | |
| Acetate | 4-5 | 4-5 | 4-5 | | | | | | | | | |
| Cotton | 4-5 | 4 | 4 | | | | | | | | | |
| Nylon | 4-5 | 4-5 | 4 | | | | | | | | | |
| Polyester | 4-5 | 4-5 | 4-5 | | | | | | | | | |
| Acrylic | 4-5 | 4-5 | 4-5 | | | | | | | | | |
| Wool | 4-5 | 4-5 | 4-5 | | | | | | | | | |
| REMARKS | Grey Scale Rating is based on the 9-step scale of 1 to 5, where 1 is bad and 5 is good | | | | | | | | | | | |

AZO

| Standard(s) | METHOD | | | | | | | | | TOLERANCE | | |
|--|---|------|------|--|--|--|--|--|--|-----------|--|--|
| EN ISO 14362-1:2017 EN ISO 14362-3:2017 | n/a | | | | | | | | | <30 mg/kg | | |
| ITEM | 001 | 002 | 003 | | | | | | | | | |
| Result (mg/kg) | N.D. | N.D. | N.D. | | | | | | | | | |
| REMARKS | 1)N.D. means the result less than MDL 5mg/kg. | | | | | | | | | | | |

LADYmate

| AZO | | | Result | | |
|--|-----------|--------------|-----------------|---------|-----------|
| Prohibitive aromatic amines | CAS NO. | Requirements | 001 | 002 | 003 |
| | | | 4-Aminodiphenyl | 92-67-1 | <30 mg/kg |
| Benzidine | 92-87-5 | <30 mg/kg | N.D. | N.D. | N.D. |
| 4-chloro-o-Toluidine | 95-69-2 | <30 mg/kg | N.D. | N.D. | N.D. |
| 2-Naphthylamine | 91-59-8 | <30 mg/kg | N.D. | N.D. | N.D. |
| o-Aminoazotoluene | 97-56-3 | <30 mg/kg | N.D. | N.D. | N.D. |
| 5-nitro-o-toluidine | 99-55-8 | <30 mg/kg | N.D. | N.D. | N.D. |
| 4-Chloroaniline | 106-47-8 | <30 mg/kg | N.D. | N.D. | N.D. |
| 4-methoxy-m-phenylenediamine | 615-05-04 | <30 mg/kg | N.D. | N.D. | N.D. |
| 4,4' -methylenedianiline | 101-77-9 | <30 mg/kg | N.D. | N.D. | N.D. |
| 3,3'-Dichlorobenzidine | 91-94-1 | <30 mg/kg | N.D. | N.D. | N.D. |
| 3,3'-Dimethoxybenzidine | 119-90-4 | <30 mg/kg | N.D. | N.D. | N.D. |
| 3,3'-Dimethylbenzidine | 119-93-7 | <30 mg/kg | N.D. | N.D. | N.D. |
| 4,4'-methylenedi-o-toluidine | 838-88-0 | <30 mg/kg | N.D. | N.D. | N.D. |
| p-cresidine | 120-71-8 | <30 mg/kg | N.D. | N.D. | N.D. |
| 4,4' -Methylene-bis-(2-Chloro-aniline) | 101-14-4 | <30 mg/kg | N.D. | N.D. | N.D. |
| 4,4'-Oxydianiline | 101-80-4 | <30 mg/kg | N.D. | N.D. | N.D. |
| 4,4'-Thiodianiline | 139-65-1 | <30 mg/kg | N.D. | N.D. | N.D. |
| o-Toluidine | 95-53-4 | <30 mg/kg | N.D. | N.D. | N.D. |
| 2,4-Diaminotoluene | 95-80-7 | <30 mg/kg | N.D. | N.D. | N.D. |
| O-Anisidine | 90-04-0 | <30 mg/kg | N.D. | N.D. | N.D. |
| 4-aminoazobenzene | 60-09-3 | <30 mg/kg | N.D. | N.D. | N.D. |
| 2,4,5-Trimethylaniline | 137-17-7 | <30 mg/kg | N.D. | N.D. | N.D. |
| 2,4-xylidine | 95-68-1 | <30 mg/kg | N.D. | N.D. | N.D. |
| 2,6-xylidine | 87-62-7 | <30 mg/kg | N.D. | N.D. | N.D. |

DESCRIPTION OF THE TEST SUBJECT(S)

| Sample | Description(Lab) | Picture |
|--------|-------------------------------------|---|
| 001 | 1M FULL WIDTH OF PRINT MICRO ABRIC |  |
| 002 | 1M FULL WIDTH OF BLUE SELVEDGE MESH |  |
| 003 | 1M FULL WIDTH OF BLUE STRETCH MESH |  |

End of Report